

► Series 3220 Overlaminates

Premium Cast Overlaminates in Gloss, Luster, Satin and Matte Finishes

Series 3220 overlaminates are constructed of 50 microns cast vinyl film with clear, permanent pressure-sensitive adhesive. Designed to protect and prolong the life of printed images, Series 3220 extends the life of the graphics by 2 years. Series 3220 is rated for outdoor durability up to 7 years. This product is not designed to be used as an optically clear window film.

APPLICATIONS & FEATURES

- Protective Overlaminates for SLX™ Cast Wrap, DPF 6100XLP, DPF 6000XRP, DPF 6000RP White, DPF 6500, DPF 6700, IllumiNITE Wrap™, DPF 2400, DPF 4600GLX, DPF 4500GT/MT, DPF 8000™ Ultra Tack, DPF 8200 High Tack, DPF 9000, DPF 4000 and DPF 4300
- Series 3220 Gloss is approved EN 14041 for slip resistance for interior floor graphics
- Long-term signage, kiosks, POP displays, fleet and vehicle applications
- Recommended dry time for printed images is 24-48 hours prior to laminating
- UV inhibitors to protect and extend the life of your printed graphic
- Arlon overlaminates film is designed to be laminated cold without any heat

PERFORMANCE & PHYSICAL DATA

PROPERTY	TEST METHODS	TYPICAL VALUE
SURFACE FINISH	Gloss Meter 60° Reflection	80 to 90 Gloss Units (Gloss) 55 to 85 Gloss Units (Luster) 20 to 30 Gloss Units (Satin) 1.5 to 10 Gloss Units (Matte)
THICKNESS	Micrometer, Federal Bench Type	50 microns
TENSILE STRENGTH	Tensile Tester with 51 mm jaw separation; crosshead speed of 5.1 mm/s, web direction	≥ 0.8 kg/cm width
ELONGATION	Instron Tensile Tester as above	≥ 150%
SHELF LIFE (IN BOX)	Ideal storage temperature 21°C and 50% relative humidity	2 years from factory shipment
APPLICATION TEMPERATURE RANGE	On clean image	4.4°C to 38°C
SERVICE TEMPERATURE RANGE	On clean, dry substrate	-40°C to 79°C
DIMENSIONAL STABILITY	Shrinkage After 70°C, 48 hours	0.12 mm
PEEL ADHESION	PSTC-1, 15 min, 21°C	0.78 kg/cm
LINER RELEASE	TLMI Release at 90°, 760 cm/min	13.78 g/cm

Standard Terms & Conditions Apply

USA

200 Boysenberry Lane, Placentia, CA 92870
 800 232 7161 / +1 714 985 6300
 +1 714 985 6305

EUROPE

Dr. Lelykade 22B, 2583CM Den Haag, The Netherlands
 +31 70 354 4311
 +31 70 355 7721

CHINA

No. 1989 Xinchang Road, Weifang, Shandong, 262400
 +86 0536 6226568

OPTIMUM PERFORMANCE

Actual weathering durability depends on surface preparation, surface maintenance and exposure conditions. Successful weather resistance is characterized by the retention of legibility. Series 3220 will resist weathering best when applied to vertical or upper outboard angles. Horizontal angles, such as hood and auto roof surfaces, will deteriorate more quickly than vertical. This is due to increased exposure to sun and moisture, as well as continued high deposition of dirt and atmospheric contaminants. Arlon does not recommend its film for horizontal or close horizontal applications. For best practice on laminating to UV inks, see [Tip 55: What is Silvering?](#)

FLOOR APPLICATION

Series 3220 Gloss is approved under the European Standard Certification EN 14041 for slip-resistance as a floor graphic material for indoor dry conditions. Arlon recommends DPF 8000™ Ultra Tack, DPF 8200 High Tack and DPF 4600GLX/MLX as the compatible media. These product combinations are recommended for short term interior floor applications, for an expected life of up to 6 months. To determine the best product for the application Arlon always recommends testing on the surface before using the above products. Product performance can vary greatly depending on the surface type, level of foot traffic, elemental exposure, the carpet type, and floor condition. Due to these variables, Arlon is unable to offer a warranty for the performance, expected life, or clean removability of these products for floor graphic applications. See Arlon's Standard Limited Warranty, which is available at https://www.arlon.com/eu_en/support/warranties

Please refer to Arlon's [Installation Guide](#) for detailed techniques and best practices.

EN 14041 - Resilient, textile and laminate floor coverings

Determination of the anti-slip properties (EN 14041) : Determination of the dynamic coefficient of friction of floor materials in accordance with EN 14041.




TERMS & CONDITIONS

The following is made in lieu of all warranties expressed or implied:




All orders and purchases made in connection with this document are governed and limited by Arlon's Standard Terms and Conditions, which are incorporated in full by this reference and are available at https://www.arlon.com/eu_en/legal/terms-and-conditions or in hardcopy by request.

August 2020 - EMEA



USA

 200 Boysenberry Lane, Placentia, CA 92870
 800 232 7161 / +1 714 985 6300
 +1 714 985 6305

EUROPE

 Dr. Lelykade 22B, 2583CM Den Haag, The Netherlands
 +31 70 354 4311
 +31 70 355 7721

CHINA

 No. 1989 Xinchang Road, Weifang, Shandong, 262400
 +86 0536 6226568