

Projection Screen Whiteboard Film PWF-500

Product Bulletin

Product Description

White calendered PVC film with hard coat. This communication film with both whiteboard and projection capabilities offers great versatility for interior application of office rooms, retail, schools and other private or public buildings. 3M Comply™ air release feature in the adhesive guarantees a fast and easy application.

The use is restricted to indoor applications on flat or moderately curved surfaces.

Product Line Communication film PWF-500 white, opaque, matte, permanent adhesive (clear)

Product Characteristics

These are typical values for unprocessed products.

Contact your 3M representative for a custom specification.

Physical & Application Material calendered vinyl (polymeric)

Surface finish matte

Thickness (film) 230 µm (0.23 mm)

Adhesive type solvent acrylic; pressure-sensitive

Adhesive appearance clear

Liner double-sided Polyethylene coated paper with Comply™ feature

Adhesion 35.5 N / 25 mm FTM 1: 180° peel, substrate: glass; cond: 24 h

23°C/50%RH

Application method dry only!

Applied shrinkage < 0.3 mm FTM 14
Application +12°C minimum (air and substrate)

temperature

Service temperature -20°C to +50°C

Surface type flat to simple curved

Substrate type aluminium, paint, galvanised steel, PVC coated steel, polyester, ABS

Graphic removal Fair to remove with heat and/or chemicals from supported substrates. No liability

is given for ease or speed of removal of any graphic. Pay attention to adequate air

and substrate temperature.

Notice For different substrates: please contact Tech Service for an adhesion test

Warranty This warranty does not apply to film problems caused by defective application and is given for unprocessed

film only!

Indoor application Film application in-side a building without direct exposure to sunlight

12 years for all areas

Durability The durability data are given for unprocessed film only!

Indoor application Film application in-side a building without direct exposure to sunlight

> 12 years; depending on frequency of use

Storage Shelf life - 2 years from the date on the original box

- up to 2 years unprocessed, or

processed within 1 year and apply within 1 year of processing

Storage conditions +4°C to +40°C, out of sunlight, original container in clean and dry area.

Flammability

Flammability standards are different from country to country. Please ask your local 3M contact for details. DIN EN 13823 European SBI. Part of the new Norm 13501-1. Results: C - s1, d0.

Limitations of End Uses

3M specifically does **not** recommend or warrant the following uses, but please contact us to discuss your needs to recommend other products.

Graphics applied to

- exterior applications.
- other than flat or moderate curved/corrugated surfaces.

Important Notice

- Wet application method is not recommended for this film.
- Do not stretch the film during application performance of hard coat will be destroyed.
- White board markers with oil based ink might be difficult to be removed.
- Printing on film is not recommended.
- Film is not intended to use with e-cut.

Graphics Manufacturing

Application

Please consult the following 3M literature for more information about

- Surface preparation: Instruction Bulletin 5.1 'Select and Prepare Substrates for Graphic Application'
- Application methods: Instruction Bulletin 5.5 'General Procedures for Interior and exterior Dry Application'

Shipping finished graphics

Flat, or rolled film side out on 130 mm (5 inch) or larger core. These methods help to prevent the liner from wrinkling or application tape, if used, from popping off.

Notice!

After installation of the film it is necessary to wipe with sufficient pressure the entire surface with the eraser to ensure proper performance. This is needed to ensure proper wet-out and adhesion of the writings. Handle the film with caution as the edges are sharp! Overlaps/butt joints are possible but not recommended for full functionality. If an overlap is needed apply primer (3M primer 94) before overlapping.

Maintenance and Cleaning

Use a cleaner designed for high-quality painted surfaces. The cleaner must be wet, non-abrasive, without strong solvents, and have a pH value between 3 and 11 (neither strongly acidic nor strongly alkaline). Refer to Instruction Bulletin 6.5 'Storage, handling, maintenance and removal of films and sheetings', for general maintenance and cleaning information.

When the film surface becomes soiled (dirt or old dried ink), wipe the surface using a soft cloth and warm water. If necessary add a mild detergent.

Notice!

Do not use permanent pens. If a permanent pen is mistakenly used, wipe off immediately with an alcohol based cleaner. This will reduce the overall performance of the film.

Writing and erasability of markings are dependent on the frequency of cleaning/erasing and overall maintenance of the film. Clean/replace the whiteboard eraser regularly.

For easiest use it is recommended to avoid having writings standing on the board for very long periods of time.

Remarks

This bulletin provides technical information only.

Important notice

All questions of warranty and liability relating to this product are governed by the terms and conditions of the sale, subject, where applicable, to the prevailing law.

Before using, the user must determine the suitability of the product for its required or intended use, and the user assumes all risk and liability whatsoever in connection therewith.

Additional information

Visit the web site of your local subsidiary at www.3M.eu/ArchitecturalMarkets for getting more:

- additional instruction bulletins
- a complete product overview about materials 3M is offering

3M Europe S.A./N.V. Hermeslaan 7 1831 Diegem, Belgium Responsible for this technical product bulletin
3M Deutschland GmbH | Display & Graphics Laboratory
Carl-Schurz-Str. 1 | 41453 Neuss, Germany

3M, Controltac, Scotchcal, Comply and MCS are trademarks of 3M Company. All other trademarks are the property of their respective owners.

The use of trademark signs and brand names in this bulletin is based upon US standards. These standards may vary from country to country outside the USA.