# Whiteboard Dryapply ASLAN WBL 995



## High quality whiteboard film for easy dry applications

The self-adhesive whiteboard film turns every surface into a writable whiteboard. The highly scratch resistant surface ensures that writings can be wiped off dry without leaving any shadows or ghostings. Fine air release channels in the adhesive allows air bubbles to be wiped out with ease, making the application fast and simple for even the most inexperienced users.

For additional information's please contact our technical advisory service:

+49 (0) 22 04. 7 08-80

#### Construction

face-film: Polyester/PVC – compound, white glossy

thickness:  $\sim 150 \, \mu m$ 

adhesive: acrylic pressure adhesive square quantity: ~ 25 g/m²

release liner: structured silicone cardboard square weight: ~ 140 g/m²

both sided PE coated

#### **Characteristics**

adhesive strength: immediately ~ 3 N/25 mm (ASTMD-903) after 1 week ~ 5 N/25 mm

dimensional stability: applied onto aluminum

after 48 hours stored at 70 °C


(25 x 25 cm) max. -0.45 %

chemical resistance: In a preece test of 24 hours the applied film is resistant to most petroleum based oils, greases and

aliphatic solvents, mild acids, alkalis and salts.

temperature: application temperature: min. 15°C

service temperature range: -30 °C up to +80 °C



Oberauel 2 · 51491 Overath · Germany · phone +49 (0) 2204.708-80 · fax +49 (0) 2204.708-50 · e-mail info@ASLAN-schwarz.com



# Whiteboard Dryapply ASLAN WBL 995



### **Processing**

application: Dry application only.

cleaning: Writings with whiteboard markers can be wiped off dry easily without leaving any

ghostings. If by mistake pens with solvent paints have been used the writings can be

wiped off with alcohol.

storage life: Before application the films can be stored for minimum 3 years from date of production.

The film must be stored at room temperature (15-25 °C) and a relative humidity of the air of 50-60%. To avoid pressure points appearing on the roll surface, we recommend the rolls be stored either vertical standing or for this purpose designed `hanging´ racks.

State: 10|2013

All technical data and advice is based on our experience and measured testing that we believe to be reliable. It remains the customer's responsibility to test the suitability of our products for the intended purpose.

The quality of our products is regularly examined, upgraded and developed. We take the right, without prior notice, to adjust, upgrade and improve the chemical structures or physical characteristics of our products in accordance with our latest knowledge.

ASLAN, Schwarz GmbH & Co. KG

Oberauel 2 · 51491 Overath · Germany · phone +49 (0) 2204.708-80 · fax +49 (0) 2204.708-50 · e-mail info@ASLAN-schwarz.com

