## WhiteboardColour ASLAN WBC 996

#### Coloured whiteboard film

The coloured whiteboard film turns every surface into a whiteboard that is writable with whiteboards markers. The highly scratch resistant surface avoids any shadows or ghosting. Therefore this self-adhesive film is ideal for applications such as daily changing menus in restaurants, seminar rooms, offices, universities and schools.

For additional information's please contact our technical advisory service:

+49 (0) 22 04. 7 08-80

#### Construction

face-film:

Polyester/PVC - compound

thickness:

~ 140 µm

adhesive:

acrylic pressure adhesive

square quantity: ~ 30 g/m<sup>2</sup>

release liner:

silicone cardboard

square weight: ~ 140 g/m<sup>2</sup>

#### **Characteristics**

adhesive strength: (ASTMD-903)

immediately after 1 week

~ 3 N/25 mm ~ 8 N/25 mm

dimensional stability:

applied onto aluminum

after 48 hours stored at 70  $^{\circ}\text{C}$ 

(25 x 25 cm)

max. -0.45 %

chemical resistance:

In a preece test of 24 hours the applied film is resistant to most petroleum based oils, greases and

aliphatic solvents, mild acids, alkalis and salts.

temperature:

application temperature: service temperature range:

min. 15°C

-30 °C up to +80 °C



Oberauel 2 · 51491 Overath · Germany · phone +49 (0) 2204.708-80 · fax +49 (0) 2204.708-50 · e-mail info@ASLAN-schwarz.com



# WhiteboardColour ASLAN WBC 996

### **Processing**

application: Dry application only.

**cleaning:** Writings with whiteboard markers can be wiped off dry easily without leaving any

ghostings. If by mistake pens with solvent paints have been used the writings can be

wiped off with alcohol.

storage life: Before application the films can be stored for minimum 3 years from date of production.

The film must be stored at room temperature (15-25  $^{\circ}$ C) and a relative humidity of the air of 50-60%. To avoid pressure points appearing on the roll surface, we recommend the rolls be stored either vertical standing or for this purpose designed `hanging´ racks.

State: 10|2013

All technical data and advice is based on our experience and measured testing that we believe to be reliable. It remains the customer's responsibility to test the suitability of our products for the intended purpose.

The quality of our products is regularly examined, upgraded and developed. We take the right, without prior notice, to adjust, upgrade and improve the chemical structures or physical characteristics of our products in accordance with our latest knowledge.

ASLAN, Schwarz GmbH & Co. KG

Oberauel 2 · 51491 Overath · Germany · phone +49 (0) 2204.708-80 · fax +49 (0) 2204.708-50 · e-mail info@ASLAN-schwarz.com

